

IFW


**PATENT**  
#03-0074-UNI  
Case #C4288(C)

**CERTIFICATE OF MAILING**

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope addressed to:

"Assistant Commissioner for Patents  
Washington, D.C. 20231"

on June 8, 2004

 06/08/04  
RIMMA MITELMAN Date of  
Reg. No. 34,396 Signature  
Attorney for Applicant(s)

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

Applicant: Gibbs et al.  
Serial No.: 10/759,417  
Filed: January 16, 2004  
For: DETERGENT COMPOSITIONS

Edgewater, New Jersey 07020  
June 8, 2004

**SUBMISSION OF PRIORITY DOCUMENT**

Assistant Commissioner for Patents  
Washington, D.C. 20231

Sir:

Pursuant to rule 55(b) of the Rules of Practice in Patent Cases, Applicant(s) is/are submitting herewith a certified copy of the United Kingdom Application No. 0301022.0 filed January 16, 2003, upon which the claim for priority under 35 U.S.C. § 119 was made in the United States.

It is respectfully requested that the priority document be made part of the file history.

Respectfully submitted,



Rimma Mitelman  
Registration No. 34,396  
Attorney for Applicant(s)

RM/mt  
(201) 840-2671



**THIS PAGE BLANK (USPTO)**



INVESTOR IN PEOPLE

The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

I also certify that the attached copy of the request for grant of a Patent (Form 1/77) bears an amendment, effected by this office, following a request by the applicant and agreed to by the Comptroller-General.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated 28 November 2003

**THIS PAGE BLANK (USPTO)**

**Request for grant of a patent**

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



17JAN03 E777703-8 D02898  
P01/7700 0.00-0301022.0

The Patent Office

Cardiff Road  
Newport  
Gwent NP10 8QQ

1. Your reference C4288 (C)/rkk

2. Patent application number 0301022.0  
(The Patent Office will fill in this part) 16 JAN 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames) UNILEVER PLC  
UNILEVER HOUSE, BLACKFRIARS  
LONDON, EC4P 4BQ

Patents ADP number (if you know it) 50426956002 ✓

If the applicant is a corporate body, give the country/state of its incorporation UNITED KINGDOM

4. Title of the invention DETERGENT COMPOSITIONS

5. Name of your agent (if you have one) ~~FRANSELLA Mary Evelyn~~ Peter William Elliott

51/77  
30/6/03  
Gm. "Address for Service" in the United Kingdom to which all correspondence should be sent (including the postcode) PATENT DEPARTMENT, UNILEVER PLC  
COLWORTH HOUSE, SHARNBROOK  
BEDFORD, MK44 1LQ

Patents ADP number (if you know it)

07171622001 1628003

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country	Priority application number (if you know it)	Date of filing (day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day/month/year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

a) any applicant named in part 3 is not an inventor, or

b) there is an inventor who is not named as an applicant, or

c) any named applicant is a corporate body. See note (d))

YES

## Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 22

Claim(s) 3 

Abstract 1

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority Documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents  
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature(s)



Date: 16/01/03

Sandra Jane EDWARDS, Authorised Signatory

12. Name and daytime telephone number of person to contact in the United Kingdom Ravinder K Kundra, Tel 01234 22 2439

### Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

### Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

DETERGENT COMPOSITIONSTECHNICAL FIELD

5

The present invention relates to laundry detergent compositions containing certain graft polymers that can reduce redeposition of soil onto fabrics during the wash process.

10

BACKGROUND AND PRIOR ART

During the laundry process in a domestic or commercial washing machine, soil is removed from the soiled fabrics by a combination of the physical action (agitation) of the machine and the detergency of the laundry detergent composition, and enters the wash liquor. A similar process occurs in handwashing. It is important to ensure that soil is not simply deposited back onto the fabrics but remains suspended in the wash liquor and eventually washed away.

Laundry detergent compositions conventionally contain sodium carboxymethyl cellulose (SCMC) as an antiredeposition agent. US 4 235 735 (Marco et al/Milliken) discloses cellulose acetates with a defined degree of substitution as antiredeposition agents in laundry detergent compositions.

Other cellulosic materials have also been used in laundry detergent compositions for a variety of benefits, for example, soil release, and fabric care benefits.

WO 00/18861A and WO 00/18862A (Unilever) disclose cellulosic compounds having a benefit agent attached, so that the benefit agent will be deposited on the fibres of the washed  
5 textiles during the laundry process.

Our pending international patent application PCT/EP02/07682 filed on 10 July 2002 discloses the use in laundry compositions of grafted polysaccharides prepared by a  
10 controlled process, the atom transfer radical polymerisation process. The polymers can give various benefits, notably soil release and fabric care benefits. Amongst the polymers disclosed as giving fabric care benefits is a polymer having a locust bean gum backbone and grafts of styrene-4-sulphonic  
15 acid.

#### DEFINITION OF THE INVENTION

20 The present invention provides a built laundry detergent composition comprising

(a) from 5 to 60 wt% of an organic detergent surfactant selected from anionic, nonionic, cationic, zwitterionic and  
25 amphoteric surfactants and combinations thereof,

(b) from 10 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of a graft polymer having a locust  
30 bean gum backbone and grafts of an aromatic sulphonic acid,



(d) optionally other detergent ingredients to 100 wt%.

The present invention further provides a particulate laundry detergent composition comprising

5

(a) from 5 to 60 wt% of an organic detergent surfactant selected from anionic, nonionic, cationic, zwitterionic and amphoteric surfactants and combinations thereof,

10 (b) optionally from 0 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of a graft polymer having a locust bean gum backbone and grafts of an aromatic sulphonic acid,

15 (d) optionally other detergent ingredients to 100 wt%.

#### DETAILED DESCRIPTION OF THE INVENTION

##### 20 The graft polymer

The graft polymer which is used in accordance with the invention to improve the antiredeposition properties of a laundry detergent composition is a polymer having a backbone  
25 of locust bean gum. Locust bean gum is a naturally occurring galactomannan polysaccharide having a beta-1,4-linked backbone.

The total number of sugar units is preferably from 50 to  
30 7000, and the preferred molecular weight is from 10 000 to 1 000 000.

In the graft polymer at least one sugar unit of the polysaccharide has been substituted with groups derived from an aromatic sulphonic acid, preferably styrene 4-sulphonic acid.

5

Thus the preferred graft polymer used in accordance with the invention is locust bean gum - graft - poly(4-styrenesulphonic acid).

10

#### Preparation of the graft polymer

The graft polymer may be prepared by any suitable process. However, according to a preferred embodiment of the invention, the polymer is prepared by the "living polymerisation" technique of atom transfer radical polymerisation (ATRP), as described and claimed in our International Patent Applications Nos. PCT/EP02/07682 and PCT/EP02/07683 filed on 10 July 2002.

20

#### The laundry detergent composition

The graft polymer is suitably incorporated in laundry detergent compositions in an amount of from 0.1 to 10 wt%, preferably from 0.5 to 5 wt%.

25

Built laundry detergent compositions utilising the graft polymer comprise:

- 5 -

(a) from 5 to 60 wt% of an organic detergent surfactant selected from anionic, nonionic, cationic, zwitterionic and amphoteric surfactants and combinations thereof,

5 (b) optionally from 0 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of the locust bean gum graft polymer,

10 (d) optionally other detergent ingredients to 100 wt%.

These compositions may be of any physical form.

for example, powder, tablet, liquid, gel, paste or bar.

15 Most preferably the laundry detergent composition is a granular or particulate composition, especially a powder or a tablet; or a liquid.

Particulate laundry detergent compositions in accordance  
20 with the invention comprise:

(a) from 5 to 60 wt% of an organic detergent surfactant selected from anionic, nonionic, cationic, zwitterionic and amphoteric surfactants and combinations thereof,

25

(b) optionally from 0 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of a graft polymer having a locust bean gum backbone and grafts of an aromatic sulphonic acid,

30

(d) optionally other detergent ingredients to 100 wt%.

The organic detergent surfactant

Detergent-active compounds (surfactants) may be chosen from soap and non-soap anionic, cationic, nonionic, amphoteric and zwitterionic detergent-active compounds, and mixtures thereof. Many suitable detergent-active compounds are available and are fully described in the literature, for example, in "Surface-Active Agents and Detergents", Volumes I and II, by Schwartz, Perry and Berch. The preferred detergent-active compounds that can be used are soaps and synthetic non-soap anionic and nonionic compounds. The total amount of surfactant present is suitably within the range of from 5 to 60 wt%, preferably from 5 to 40 wt%.

Anionic surfactants are well-known to those skilled in the art. Examples include alkylbenzene sulphonates, particularly linear alkylbenzene sulphonates having an alkyl chain length of C<sub>8</sub>-C<sub>15</sub>; primary and secondary alkylsulphates, particularly C<sub>8</sub>-C<sub>20</sub> primary alkyl sulphates; alkyl ether sulphates; olefin sulphonates; alkyl xylene sulphonates; dialkyl sulphosuccinates; and fatty acid ester sulphonates. Sodium salts are generally preferred. Nonionic surfactants that may be used include the primary and secondary alcohol ethoxylates, especially the C<sub>8</sub>-C<sub>20</sub> aliphatic alcohols ethoxylated with an average of from 1 to 20 moles of ethylene oxide per mole of alcohol, and more especially the C<sub>10</sub>-C<sub>15</sub> primary and secondary aliphatic alcohols ethoxylated with an average of from 1 to 10 moles of ethylene oxide per mole of alcohol. Non-ethoxylated nonionic surfactants include alkanolamides,

alkylpolyglycosides, glycerol monoethers, and polyhydroxyamides (glucamide).

Cationic surfactants that may be used include quaternary ammonium salts of the general formula  $R_1R_2R_3R_4N^+ X^-$  wherein the R groups are long or short hydrocarbyl chains, typically alkyl, hydroxyalkyl or ethoxylated alkyl groups, and X is a solubilising anion (for example, compounds in which  $R_1$  is a  $C_8$ - $C_{22}$  alkyl group, preferably a  $C_8$ - $C_{10}$  or  $C_{12}$ - $C_{14}$  alkyl group,  $R_2$  is a methyl group, and  $R_3$  and  $R_4$ , which may be the same or different, are methyl or hydroxyethyl groups); and cationic esters (for example, choline esters).

Amphoteric and zwitterionic surfactants that may be used include alkyl amine oxides, betaines and sulphobetaines. In accordance with the present invention, the detergent surfactant (a) most preferably comprises an anionic sulphonate or sulphonate surfactant optionally in admixture with one or more cosurfactants selected from ethoxylated nonionic surfactants, non-ethoxylated nonionic surfactants, ethoxylated sulphate anionic surfactants, cationic surfactants, amine oxides, alkanolamides and combinations thereof.

Surfactants are preferably present in a total amount of from 5 to 60 wt%, more preferably from 10 to 40 wt%.

The detergency builder

Preferred inorganic builders are alkali metal aluminosilicates, more especially crystalline alkali metal aluminosilicates (zeolites), preferably in sodium salt form.

Zeolite builders may suitably be present in a total amount of from 5 to 60 wt%, preferably from 10 to 50 wt%.

10 The zeolites may be supplemented by other inorganic builders, for example, amorphous aluminosilicates, or layered silicates such as SKS-6 ex Clariant.

The zeolites may be supplemented by organic builders, for example, polycarboxylate polymers such as polyacrylates and acrylic/maleic copolymers; monomeric polycarboxylates such as citrates, gluconates, oxydisuccinates, glycerol mono-, di- and trisuccinates, carboxymethyloxysuccinates, carboxymethyloxymalonates, dipicolinates, hydroxyethyliminodiacetates, alkyl- and alkenylmalonates and succinates; and sulphonated fatty acid salts.

Alternatively, the compositions of the invention may contain phosphate builders, for example, sodium tripolyphosphate.

25

Especially preferred organic builders are citrates, suitably used in amounts of from 1 to 30 wt%, preferably from 2 to 15 wt%; and acrylic polymers, more especially acrylic/maleic copolymers, suitably used in amounts of from 0.5 to 15 wt%, preferably from 1 to 10 wt%. Builders, both

inorganic and organic, are preferably present in alkali metal salt, especially sodium salt, form.

Builders are suitably present in total amounts of from 10 to 80 wt%, more preferably from 20 to 60 wt%. Builders may be inorganic or organic.

A built composition in accordance with the invention may most preferably comprise from 10 to 80 wt% of a detergency builder (b) selected from zeolites, phosphates, and citrates.

#### Other detergent ingredients

15

The laundry detergent composition will generally comprises other detergent ingredients well known in the art.

These may suitably be selected from bleach ingredients, enzymes, sodium carbonate, sodium silicate, sodium sulphate, foam controllers, foam boosters, perfumes, fabric conditioners, soil release polymers, dye transfer inhibitors, photobleaches, fluorescers and coloured speckles.

25 Detergent compositions in accordance with the invention may also suitably contain a bleach system. Preferably this will include a peroxy bleach compound, for example, an inorganic persalt or an organic peroxyacid, capable of yielding hydrogen peroxide in aqueous solution.

30

Preferred inorganic persalts are sodium perborate monohydrate and tetrahydrate, and sodium percarbonate, the latter being especially preferred. The sodium percarbonate may have a protective coating against destabilisation by moisture. The peroxy bleach compound is suitably present in an amount of from 5 to 35 wt%, preferably from 10 to 25 wt%.

The peroxy bleach compound may be used in conjunction with a bleach activator (bleach precursor) to improve bleaching action at low wash temperatures. The bleach precursor is suitably present in an amount of from 1 to 8 wt%, preferably from 2 to 5 wt%. Preferred bleach precursors are peroxycarboxylic acid precursors, more especially peracetic acid precursors and peroxybenzoic acid precursors; and peroxycarbonic acid precursors. An especially preferred bleach precursor is N,N,N',N'-tetracetyl ethylenediamine (TAED).

A bleach stabiliser (heavy metal sequestrant) may also be present. Suitable bleach stabilisers include ethylenediamine tetraacetate (EDTA), diethylenetriamine pentaacetate (DTPA), ethylenediamine disuccinate (EDDS), and the polyphosphonates such as the Dequests (Trade Mark), ethylenediamine tetramethylene phosphonate (EDTMP) and diethylenetriamine pentamethylene phosphate (DETPMP).

Compositions of the invention in particulate form may contain alkali metal, preferably sodium, carbonate, in order to increase detergency and ease processing. Sodium carbonate may suitably be present in amounts ranging from 1 to 60 wt%, preferably from 2 to 40 wt%.



As previously indicated, sodium silicate may also be present. The amount of sodium silicate may suitably range from 0.1 to 5 wt%.

5

#### Preparation of particulate detergent composition

Particulate detergent compositions are suitably prepared by spray-drying a slurry of compatible heat-insensitive ingredients in a spray-drying tower, and then spraying on or postdosing those ingredients unsuitable for processing via the slurry. The skilled detergent formulator will have no difficulty in deciding which ingredients should be included in the slurry and which should not.

15

If a high bulk density is desired, the spray-dried detergent composition may be subjected to post-tower densification using, for example, a high-speed mixer/granulator.

Alternatively, particulate detergent compositions may be prepared by wholly non-tower mixing and granulation processes. In both cases a high-speed mixer/granulator may advantageously be used.

25

#### EXAMPLES

The invention is further illustrated by the following non-limiting Examples, in which parts and percentages are by weight unless otherwise stated.


30

EXAMPLE 1: SYNTHESIS OF GRAFT POLYMER1.1 Preparation of locust bean gum macroinitiator

5

A 9% w/v solution of lithium chloride (LiCl) in N,N-dimethylsulphoxide (DMSO) was prepared by heating 18g of LiCl in 200cm<sup>3</sup> of anhydrous DMSO to 150°C in a 2-necked round bottom flask fitted with an overhead stirrer. Once a  
10 homogeneous solution had been obtained, Locust Bean Gum (LBG, MUD 246B ex Rhodia) (10g, 0.062 mol of anhydromannose/galactose unit) was added to the solution gradually, maintaining the temperature at 150°C until a highly viscous, clear, yellow solution had formed. This  
15 solution was then cooled to 65°C.

In a separate beaker, a solution of 2-bromoisobutyric acid (10g, 0.06mol) in anhydrous DMSO (50cm<sup>3</sup>) was prepared. To this solution, 1,1'-carbonyldiimidazole (CDI) (10g, 0.00617  
20 mol) was added slowly. Once the evolution of CO<sub>2</sub> had ceased, this solution was added to the LBG/DMSO/LiCl solution with stirring. The reaction mixture was maintained at 65°C for 24 hours. It was then poured into a threefold volume of methanol, causing the product to precipitate. This was  
25 collected on a sinter funnel, then re-dispersed into methanol, filtered and washed with copious amounts of methanol. The product was dried under vacuo at 60°C for 48 hours, yielding 8g of a creamy, crystalline solid.

Reaction scheme 1:5 Characterisation:

IR :  $1736\text{ cm}^{-1}$  (s, saturated ester carbonyl)

NMR ( $^1\text{H}-\text{D}_2\text{O}$ ) : 1.84 (d, ester  $\text{CH}_3$ , 6H);


3.4-4.6 (m, mannose/galactose CH and  $\text{CH}_2$ , 90H)

- 10 From the nmr, the average degree of substitution (DS) is 1 ester group for every 15 Locust Bean Gum sugar rings .

1.2 Preparation of Locust Bean Gum - graft - poly(sodium 4-styrenesulphonic acid)

To a 3-necked round bottom flask fitted with a N<sub>2</sub> inlet and  
5 outlet and a thermometer were added Locust Bean Gum-  
macroinitiator (3g,  $1.19 \times 10^{-3}$  mol), sodium 4-styrenesulphonic  
acid (12.31g, 0.0597 mol) and a magnetic stirrer bar. The  
solids were dissolved in demineralised water (50 cm<sup>3</sup>) and the  
resulting solution de-gassed by bubbling nitrogen gas  
10 through for 45 minutes. A mixture of copper (I) bromide  
(0.1713g,  $1.19 \times 10^{-3}$  mol) and 2,2'-dipyridyl (0.3773g,  
 $2.39 \times 10^{-3}$  mol) was added to the reaction flask. A  
polymerisation exotherm of 10°C was noted.

15 The reaction was stirred for 2 hours at ambient temperature.  
The contents of the flask was then diluted with  
demineralised water and the solution passed through a bed of  
silica on a sinter funnel, yielding a water-white, clear  
solution. This was added to a threefold volume of methanol,  
20 causing the product to precipitate. This was collected on a  
filter and dried in vacuo at 40°C to constant weight,  
yielding 8g of white, crystalline powder.

Reaction scheme 2 :Characterisation :

5

NMR ( $^1\text{H}$ -D<sub>2</sub>O)/ppm: 0.9-2.4 (bm, vinylic polymer backbone);  
 3.2-4.4 (bm, mannose/galactose CH's and CH<sub>2</sub>'s); 6.1-7.0 (bm)  
 and 7.3-7.9 (bm, aryl CH's).

10

EXAMPLE 2: ANTIREDEPOSITION BENEFITSMethod of measuring redeposition

- 5 The method involved the use of a tergotometer and multiple washing in order to simulate the redeposition process that occurs with repeated washing either under difficult wash conditions or with low efficiency wash products.
- 10 Test formulations were used to wash pre-soiled "test cloths" together with clean fabrics (redeposition monitors) under standard conditions. The soiled fabrics were used to supply soil to the system and also to measure the cleaning efficiency of the formulations. The clean fabrics were used
- 15 to "collect" soil from the liquor and were used to quantify the level of soil redeposition. After washing, the test cloths and redeposition monitors were dried and their reflectance measured. A new batch of test cloths was then washed together with the redeposition monitors from the
- 20 original wash cycle and the process repeated to give information on the level of redeposition after two wash cycles. This process was then repeated for a third, fourth (etc) wash cycle:
- 25 Cycle 1: test cloths, clean antiredeposition monitors  
Cycle 2: test cloths, antiredeposition monitors from Cycle 1  
Cycle 3: test cloths, antiredeposition monitors from Cycle 2  
Cycle 4: test cloths, antiredeposition monitors from Cycle 3  
...
- 30 Cycle n: test cloths, antiredeposition monitors from Cycle n-1

This protocol allows both the detergency and the redeposition process to be followed as a function of cycle number. The reflectance value falls with successive cycles as more soil is present in the system: the smaller the reflectance decrease, the better the antiredeposition properties of the formulation.

#### Test formulations

- 10 A stock solution was prepared, using water of 40 degrees French hardness, containing 2 g/l of the following notional formulation (equivalent to 1.77 g/l of the specified ingredients other than water):

Ingredient	Weight%
Sodium linear alkylbenzene sulphonate LAS (100%)	26.00
Sodium tripolyphosphate	24.02
Sodium sulphate	18.14
Sodium carbonate	10.85
Sodium alkaline silicate (48%) as 100% by weight	4.66
(Water	to 100)

The following formulations were tested:

Example	
Comparative Example A	Formulation as above
Comparative Example B	Formulation as above plus 1.5 wt% of sodium carboxymethyl cellulose
Example 2	Formulation as above plus 1.5 wt% of the polymer of Example 1

For each product tested there were 3 replicates.

5

#### Test cloths

The soiled test cloths (detergency monitors) were 7.5 cm x

10 7.5 cm squares as follows:

Fabric	Soil
Cotton	Nut oil and iron oxide (black)
Cotton	Kaolin and sebum
Polyester	Kaolin and sebum
Cotton	Carbon black and mineral oil

The clean test cloths (antiredeposition monitors) were 10 cm x 10 cm squares of the following fabrics:

15

knitted cotton

woven cotton

polyester

20



- 19 -

Test wash procedure

- The tergotometer pots containing the test formulations, soiled and clean test cloths at 25°C were agitated at 90 rpm for 15 minutes. The fabric bundles were then removed from the pots and rinsed twice in water (40 degrees French hard). the fabrics were then dried in the dark for at least 12 hours.
- 10 The reflectance values of the redeposition monitors were measured (full spectrum with ultraviolet) excluded) before and after the wash.

The procedure was repeated for 8 cycles and reflectance measured at the end of each cycle.

Redeposition results

- 20 The following table shows mean reflectance values after 3 wash cycles:

Example	Antiredeposition agent	Number of replicates	Reflectance change $\Delta R_{460}$
A	None	3	-4.87
B	SCMC	6	-3.19
2	Example 1 polymer	3	-2.50

EXAMPLES 3 TO 6LAUNDRY DETERGENT FORMULATIONS

The following are examples of laundry detergent formulations  
5 in accordance with the invention.

Example 3: Laundry liquid

Ingredient	wt%
monoethanolamine	0.23
sodium citrate	3.20
coconut fatty acid	0.77
sodium linear alkylbenzene sulphonate	6.00
nonionic surfactant (alcohol ethoxylate, 9EO)	6.60
sodium lauryl ether sulphate	10.50
propylene glycol	4.75
sorbitol	3.35
borax	2.30
polymer of Example 1	1.5
fluorescer	0.125
polymer, acrylate/styrene	0.30
protease, lipase	0.70
perfume	0.2
Water	to 100

Example 4: non-phosphate heavy duty laundry powder

Ingredient	wt %
Na linear alkylbenzene sulphonate (as 100 %)	8.4
Nonionic surfactant 7EO	6.5
Na carbonate	11.7
Zeolite MAP (anhydrous basis)	21.6
Na sulphate	14.5
Na silicate (as 100%)	0.85
Soap	1.47
Tetraacetyl ethylene diamine (83%)	2.71
Na percarbonate	15.00
Ethylenediamine tetramethylene phosphonate	0.72
Na carbonate/silicate cogranule	3.6
Antifoam granule	1.22
Moisture & salts	5.17
Polymer of Example 1	1.5
Soil release polymer (sulphonated polyester)	0.12
Anti dye transfer polymer (polyvinyl pyrrolidone)	0.08
Acrylic/maleic copolymer	1.3
Fluorescer, enzymes (protease, lipase, amylase, cellulase), perfumes, minor ingredients	to 100

Examples 5 and 6: laundry tablets

Ingredient	Example 5 Non-phosphate tablet	Example 6 Phosphate tablet
Na linear alkylbenzene sulphonate	9.33	9.48
Nonionic surfactant	4.1	4.19
Soap	0.73	0.29
Sodium tripolyphosphate	-	51.00
zeolite MAP (anhydrous basis)	20.86	-
Na citrate	2.5	-
Na acetate	26.43	-
Na carbonate	3.1	-
Na disilicate (as 100%)	2.0	3.48
Antifoam granule (100%)	0.3	0.425
Na percarbonate (100%)	13.35	12.46
Tetraacetyl ethylenediamine (100%)	4.2	2.35
Ethylenediamine tetramethylene phosphonate	0.34	0.46
Polyvinyl pyrrolidone (100%)	0.19	0.143
Soil release polymer (sulphonated polyester)	0.25	0.11
Polymer of Example 1	1.5	1.5
Enzymes (protease, lipase, cellulase), fluorescer, perfume, minor ingredients, water	to 100	to 100

CLAIMS

1 A built laundry detergent composition comprising

5

(a) from 5 to 60 wt% of an organic detergent surfactant selected from anionic, nonionic, cationic, zwitterionic and amphoteric surfactants and combinations thereof,

10 (b) from 10 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of a graft polymer having a locust bean gum backbone and grafts of an aromatic sulphonic acid,

15 (d) optionally other detergent ingredients to 100 wt%.

2 A detergent composition as claimed in claim 1, wherein the laundry detergent composition is a granular or  
20 particulate composition.

3 A detergent composition as claimed in claim 1, wherein the laundry detergent composition is a liquid.

25

4 A particulate laundry detergent composition comprising

(a) from 5 to 60 wt% of an organic detergent surfactant  
selected from anionic, nonionic, cationic, zwitterionic and  
5 amphoteric surfactants and combinations thereof,

(b) optionally from 0 to 80 wt% of a detergency builder,

(c) from 0.1 to 10 wt% of a graft polymer having a locust  
10 bean gum backbone and grafts of an aromatic sulphonic acid,

(d) optionally other detergent ingredients to 100 wt%.

15 5 A laundry detergent composition as claimed in any  
preceding claim, wherein the graft polymer is locust bean  
gum - graft - poly(4-styrenesulphonic acid).

20 6 A detergent composition as claimed in any preceding  
claim, wherein the organic detergent surfactant (a)  
comprises an anionic sulphonate or sulphonate surfactant  
optionally in admixture with one or more cosurfactants  
selected from ethoxylated nonionic surfactants, non-  
25 ethoxylated nonionic surfactants, ethoxylated sulphate  
anionic surfactants, cationic surfactants, amine oxides,  
alkanolamides and combinations thereof.

30 7 A detergent composition as claimed in any preceding  
claim, which comprises a detergency builder (b) selected  
from zeolites, phosphates, and citrates.

8 A detergent composition as claimed in any preceding claim, wherein the laundry detergent composition comprises other detergent ingredients (d) selected from bleach ingredients, enzymes, sodium carbonate, sodium silicate,

5 sodium sulphate, foam controllers, foam boosters, perfumes, fabric conditioners, soil release polymers, dye transfer inhibitors, photobleaches, fluorescers and coloured speckles.

ABSTRACT

5 Incorporation in a laundry detergent composition of a graft  
polymer having a locust bean gum backbone and grafts of an  
aromatic sulphonic acid improves antiredeposition  
properties. The preferred polymer is locust bean gum -  
graft - poly(4-styrenesulphonic acid).